Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: CP-2020-12-30-78 **Date: 16/12/2020**

: Construction of Ward Office in Ward No.05, Byatarayanapura

: Sri.S K Keshavamurthy, #104, Sampigehalli, Jakkur Post, Bangalore-560064

: EE(Project)/Ynk Zone/WO/97/2020-21

: 11-12-20

: GF Staircase Concrete

: 150X150X150 mm

: M25 / 7 Days Compressive Strength

: IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 16/12/2020

Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
M25	09/12/2020	16/12/2020	149.79 X 149.63 X 149.12	22414	**8.772**	522.7	23.3	22.8
M25	09/12/2020	16/12/2020	149.08 X 150.52 X 151.86	22440	**8.381**	502.8	22.4	
M25	09/12/2020	16/12/2020	151.82 X 149.88 X 150.33	22756	**8.828**	513.9	22.6	

satisfactory as per standard requirements.

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

| Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: CP-2020-12-30-78 **Date: 06/01/2021**

: Construction of Ward Office in Ward No.05, Byatarayanapura

: Sri.S K Keshavamurthy, #104, Sampigehalli, Jakkur Post, Bangalore-560064

: EE(Project)/Ynk Zone/WO/97/2020-21

: 11-12-20

: GF Staircase Concrete

: 150X150X150 mm

: M25 / 28 Days Compressive Strength

: IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 06/01/2021

Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
M25	09/12/2020	06/01/2021	151.67 X 151.52 X 149.49	22980	**8.810**	636.8	27.7	27.5
M25	09/12/2020	06/01/2021	149.59 X 150.44 X 150.21	22504	**8.575**	591.0	26.3	
M25	09/12/2020	06/01/2021	151.41 X 151.40 X 149.94	22923	**8.480**	650.7	28.4	

satisfactory as per standard requirements.

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

4526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: CP-2020-12-30-78 **Date: 16/12/2020**

: Construction of Ward Office in Ward No.05, Byatarayanapura

: Sri.S K Keshavamurthy, #104, Sampigehalli, Jakkur Post, Bangalore-560064

: EE(Project)/Ynk Zone/WO/97/2020-21

: 11-12-20

: GF Roof Concrete

: 150X150X150 mm

: M25 / 7 Days Compressive Strength

: IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 16/12/2020

Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
M25	09/12/2020	16/12/2020	151.86 X 149.61 X 149.01	22719	8.772	526.0	23.2	22.9
M25	09/12/2020	16/12/2020	150.25 X 150.33 X 149.35	22587	8.381	507.8	22.5	
M25	09/12/2020	16/12/2020	150.97 X 150.06 X 151.64	22654	8.828	520.8	23.0	

satisfactory as per standard requirements.

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: **CP-2020-12-30-78** **Date: 06/01/2021**

: Construction of Ward Office in Ward No.05, Byatarayanapura

: Sri.S K Keshavamurthy, #104, Sampigehalli, Jakkur Post, Bangalore-560064

: EE(Project)/Ynk Zone/WO/97/2020-21

: 11-12-20

: GF Roof Concrete

: 150X150X150 mm

: M25 / 28 Days Compressive Strength

: IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 06/01/2021

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
GF Roof Concrete	M25	09/12/2020	06/01/2021	150.20 X 149.86 X 150.58	22508	**8.810**	612.2	27.2	27.4
GF Roof Concrete	M25	09/12/2020	06/01/2021	151.19 X 149.97 X 150.93	22674	**8.575**	606.3	26.7	
GF Roof Concrete	M25	09/12/2020	06/01/2021	149.38 X 150.73 X 149.97	22516	**8.480**	639.4	28.4	

Results obtained are satisfactory as per standard requirements.

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: CP-2020-12-30-78 **Date: 16/12/2020**

: Construction of Ward Office in Ward No.05, Byatarayanapura

: Sri.S K Keshavamurthy, #104, Sampigehalli, Jakkur Post, Bangalore-560064

: EE(Project)/Ynk Zone/WO/97/2020-21

: 11-12-20

: GF Roof Concrete

: 150X150X150 mm

: M25 / 7 Days Compressive Strength

: IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 16/12/2020

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
GF Roof Concrete	M25	09/12/2020	16/12/2020	149.77 X 150.72 X 150.24	22573	**8.772**	532.7	23.6	23.0
GF Roof Concrete	M25	09/12/2020	16/12/2020	149.84 X 150.33 X 149.49	22526	**8.381**	510.7	22.7	
GF Roof Concrete	M25	09/12/2020	16/12/2020	151.38 X 151.05 X 150.18	22867	**8.828**	520.4	22.8	

Satisfactory as per standard requirements.

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: **CP-2020-12-30-78** **Date: 06/01/2021**

: Construction of Ward Office in Ward No.05, Byatarayanapura

: Sri.S K Keshavamurthy, #104, Sampigehalli, Jakkur Post, Bangalore-560064

: EE(Project)/Ynk Zone/WO/97/2020-21

: 11-12-20

: GF Roof Concrete

: 150X150X150 mm

: M25 / 28 Days Compressive Strength

: IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 06/01/2021

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
Roof Concrete	M25	09/12/2020	06/01/2021	151.10 X 151.55 X 151.30	22900	**8.810**	628.9	27.5	27.3
Roof Concrete	M25	09/12/2020	06/01/2021	151.58 X 149.25 X 150.49	22623	**8.575**	594.6	26.3	
Roof Concrete	M25	09/12/2020	06/01/2021	149.14 X 149.50 X 151.45	22296	**8.480**	629.5	28.2	

are satisfactory as per standard requirements.

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R.KARTHIK RECHAN
Authorized Signatory
Quality Manager

Page 1/1
****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: **CP-2020-12-30-78** **Date: 16/12/2020**

: Construction of Ward Office in Ward No.05, Byatarayanapura

: Sri.S K Keshavamurthy, #104, Sampigehalli, Jakkur Post, Bangalore-560064

: EE(Project)/Ynk Zone/WO/97/2020-21

: 11-12-20

: GF Roof Concrete

: 150X150X150 mm

: M25 / 7 Days Compressive Strength

: IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 16/12/2020

	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
	M25	09/12/2020	16/12/2020	149.86 X 151.34 X 149.42	22680	**8.772**	524.6	23.1	23.0
	M25	09/12/2020	16/12/2020	151.65 X 149.61 X 149.20	22687	**8.381**	520.5	22.9	
	M25	09/12/2020	16/12/2020	151.39 X 150.75 X 150.61	22821	**8.828**	522.3	22.9	

satisfactory as per standard requirements.

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R.KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: **CP-2020-12-30-78** **Date: 06/01/2021**

: Construction of Ward Office in Ward No.05, Byatarayanapura

: Sri.S K Keshavamurthy, #104, Sampigehalli, Jakkur Post, Bangalore-560064

: EE(Project)/Ynk Zone/WO/97/2020-21

: 11-12-20

: GF Roof Concrete

: 150X150X150 mm

: M25 / 28 Days Compressive Strength

: IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 06/01/2021

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
Roof Concrete	M25	09/12/2020	06/01/2021	150.91 X 150.93 X 149.07	22777	**8.810**	630.5	27.7	27.3
Roof Concrete	M25	09/12/2020	06/01/2021	150.84 X 151.88 X 149.80	22909	**8.575**	601.8	26.3	
Roof Concrete	M25	09/12/2020	06/01/2021	149.44 X 151.55 X 150.33	22647	**8.480**	635.1	28.0	

are satisfactory as per standard requirements.

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Page 1/1
****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: **CP-2020-12-30-78** **Date: 16/12/2020**

: Construction of Ward Office in Ward No.05, Byatarayanapura

: Sri.S K Keshavamurthy, #104, Sampigehalli, Jakkur Post, Bangalore-560064

: EE(Project)/Ynk Zone/WO/97/2020-21

: 11-12-20

: GF Roof Concrete

: 150X150X150 mm

: M25 / 7 Days Compressive Strength

: IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 16/12/2020

Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
M25	09/12/2020	16/12/2020	150.72 X 151.42 X 151.09	22822	**8.772**	544.4	23.9	22.8
M25	09/12/2020	16/12/2020	149.66 X 151.11 X 149.58	22614	**8.381**	500.8	22.1	
M25	09/12/2020	16/12/2020	149.84 X 150.34 X 149.30	22527	**8.828**	506.6	22.5	

satisfactory as per standard requirements.

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Page 1/1
****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: CP-2020-12-30-78 **Date: 06/01/2021**

: Construction of Ward Office in Ward No.05, Byatarayanapura

: Sri.S K Keshavamurthy, #104, Sampigehalli, Jakkur Post, Bangalore-560064

: EE(Project)/Ynk Zone/WO/97/2020-21

: 11-12-20

: GF Roof Concrete

: 150X150X150 mm

: M25 / 28 Days Compressive Strength

: IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 06/01/2021

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
Roof Concrete	M25	09/12/2020	06/01/2021	150.85 X 150.22 X 150.65	22662	8.810	628.1	27.7	27.8
Roof Concrete	M25	09/12/2020	06/01/2021	151.69 X 149.69 X 149.53	22707	8.575	609.2	26.8	
Roof Concrete	M25	09/12/2020	06/01/2021	150.02 X 150.46 X 149.18	22572	8.480	650.7	28.8	

are satisfactory as per standard requirements.

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 29/12/2020

: CP-2020-12-30-78

: Construction of Ward Office in Ward No.05, Byatarayanapura

: Sri.S K Keshavamurthy, #104, Sampigehalli, Jakkur Post, Bangalore-560064

: EE(Project)/Ynk Zone/WO/97/2020-21

: 24-12-20

: FF Column Concrete

: 150X150X150 mm

: M25 / 7 Days Compressive Strength

: IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 29/12/2020

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm²)	Average Compressive Strength (N/mm²)
Column Concrete	M25	22/12/2020	29/12/2020	150.60 X 150.15 X 151.22	22613	8.772	525.7	23.2	22.7
Column Concrete	M25	22/12/2020	29/12/2020	150.42 X 150.51 X 151.21	22640	8.381	499.1	22.0	
Column Concrete	M25	22/12/2020	29/12/2020	149.26 X 149.81 X 149.72	22359	8.828	508.5	22.7	

are satisfactory as per standard requirements.

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: **CP-2020-12-30-78** **Date: 19/01/2021**

: Construction of Ward Office in Ward No.05, Byatarayanapura

: Sri.S K Keshavamurthy, #104, Sampigehalli, Jakkur Post, Bangalore-560064

: EE(Project)/Ynk Zone/WO/97/2020-21

: 24-12-20

: FF Column Concrete

: 150X150X150 mm

: M25 / 28 Days Compressive Strength

: IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 19/01/2021

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
Column Concrete	M25	22/12/2020	19/01/2021	149.90 X 149.42 X 151.80	22398	**8.810**	606.8	27.1	27.3
Column Concrete	M25	22/12/2020	19/01/2021	149.94 X 150.42 X 149.19	22555	**8.575**	590.3	26.2	
Column Concrete	M25	22/12/2020	19/01/2021	150.96 X 149.80 X 151.18	22613	**8.480**	644.7	28.5	

are satisfactory as per standard requirements.

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

24526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: CP-2020-12-30-78 **Date: 16/01/2021**

: Construction of Ward Office in Ward No.05, Byatarayanapura

: Sri.S K Keshavamurthy, #104, Sampigehalli, Jakkur Post, Bangalore-560064

: EE(Project)/Ynk Zone/WO/97/2020-21

: 11-01-21

: FF Staircase Concrete

: 150X150X150 mm

: M25 / 7 Days Compressive Strength

: IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 16/01/2021

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
FF Staircase Concrete	M25	09/01/2021	16/01/2021	149.14 X 150.26 X 151.87	22410	**8.772**	525.1	23.4	23.0
FF Staircase Concrete	M25	09/01/2021	16/01/2021	151.55 X 150.18 X 151.77	22758	**8.381**	519.7	22.8	
FF Staircase Concrete	M25	09/01/2021	16/01/2021	149.68 X 149.47 X 150.08	22374	**8.828**	505.4	22.6	

Results obtained are satisfactory as per standard requirements.

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: **CP-2020-12-30-78** **Date: 06/02/2021**

: Construction of Ward Office in Ward No.05, Byatarayanapura

: Sri.S K Keshavamurthy, #104, Sampigehalli, Jakkur Post, Bangalore-560064

: EE(Project)/Ynk Zone/WO/97/2020-21

: 11-01-21

: FF Staircase Concrete

: 150X150X150 mm

: M25 / 28 Days Compressive Strength

: IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 06/02/2021

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
FF Staircase Concrete	M25	09/01/2021	06/02/2021	151.02 X 149.77 X 149.28	22618	**8.810**	623.8	27.6	27.6
FF Staircase Concrete	M25	09/01/2021	06/02/2021	150.08 X 150.47 X 151.36	22583	**8.575**	601.1	26.6	
FF Staircase Concrete	M25	09/01/2021	06/02/2021	150.63 X 151.50 X 149.37	22821	**8.480**	652.6	28.6	

are satisfactory as per standard requirements.

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: CP-2020-12-30-78

Date: 16/01/2021

: Construction of Ward Office in Ward No.05, Byatarayanapura

: Sri.S K Keshavamurthy, #104, Sampigehalli, Jakkur Post, Bangalore-560064

: EE(Project)/Ynk Zone/WO/97/2020-21

: 11-01-21

: FF Staircase Concrete

: 150X150X150 mm

: M25 / 7 Days Compressive Strength

: IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 16/01/2021

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
FF Staircase Concrete	M25	09/01/2021	16/01/2021	149.93 X 150.25 X 150.83	22527	**8.772**	519.8	23.1	22.7
FF Staircase Concrete	M25	09/01/2021	16/01/2021	150.18 X 150.27 X 149.64	22567	**8.381**	497.8	22.1	
FF Staircase Concrete	M25	09/01/2021	16/01/2021	150.70 X 151.88 X 150.16	22889	**8.828**	526.0	23.0	

are satisfactory as per standard requirements.

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: **CP-2020-12-30-78** **Date: 06/02/2021**

: Construction of Ward Office in Ward No.05, Byatarayanapura

: Sri.S K Keshavamurthy, #104, Sampigehalli, Jakkur Post, Bangalore-560064

Reference : EE(Project)/Ynk Zone/WO/97/2020-21

: 11-01-21

: FF Staircase Concrete

Type /Size : 150X150X150 mm

grade/Age : M25 / 28 Days Compressive Strength

BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 06/02/2021

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
FF Staircase Concrete	M25	09/01/2021	06/02/2021	150.40 X 151.98 X 151.70	22858	**8.810**	638.4	27.9	27.7
FF Staircase Concrete	M25	09/01/2021	06/02/2021	151.73 X 151.35 X 149.29	22963	**8.575**	605.0	26.3	
FF Staircase Concrete	M25	09/01/2021	06/02/2021	151.54 X 150.56 X 150.37	22816	**8.480**	660.3	28.9	

tained are satisfactory as per standard requirements.

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: CP-2020-12-30-78 **Date: 16/01/2021**

: Construction of Ward Office in Ward No.05, Byatarayanapura

: Sri.S K Keshavamurthy, #104, Sampigehalli, Jakkur Post, Bangalore-560064

Reference : EE(Project)/Ynk Zone/WO/97/2020-21

: 11-01-21

: FF Roof Concrete

Type /Size : 150X150X150 mm

grade/Age : M25 / 7 Days Compressive Strength

to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 16/01/2021

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
Roof Concrete	M25	09/01/2021	16/01/2021	149.09 X 149.99 X 151.58	22363	**8.772**	533.1	23.8	22.9
Roof Concrete	M25	09/01/2021	16/01/2021	150.35 X 150.93 X 150.25	22692	**8.381**	502.1	22.1	
Roof Concrete	M25	09/01/2021	16/01/2021	151.27 X 151.21 X 150.11	22874	**8.828**	521.2	22.8	

tained are satisfactory as per standard requirements.

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-12-30-78** **Date: 06/02/2021**

Project Name : Construction of Ward Office in Ward No.05, Byatarayanapura

Owner : Sri.S K Keshavamurthy, #104, Sampigehalli, Jakkur Post, Bangalore-560064

Customer's Reference : EE(Project)/Ynk Zone/WO/97/2020-21

Date of Receipt : 11-01-21

Customer ID : FF Roof Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 06/02/2021

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	FF Roof Concrete	M25	09/01/2021	06/02/2021	151.31 X 151.60 X 150.68	22939	**8.810**	620.4	27.0	27.5
2	FF Roof Concrete	M25	09/01/2021	06/02/2021	151.49 X 149.48 X 151.48	22645	**8.575**	606.2	26.8	
3	FF Roof Concrete	M25	09/01/2021	06/02/2021	150.19 X 151.09 X 150.10	22693	**8.480**	652.7	28.8	

Results obtained are satisfactory as per standard requirements.

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-12-30-78** **Date: 16/01/2021**

Project Name : Construction of Ward Office in Ward No.05, Byatarayanapura

Agency : Sri.S K Keshavamurthy, #104, Sampigehalli, Jakkur Post, Bangalore-560064

Customer's Reference : EE(Project)/Ynk Zone/WO/97/2020-21

Date of Receipt : 11-01-21

Customer ID : FF Roof Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 16/01/2021

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	FF Roof Concrete	M25	09/01/2021	16/01/2021	151.30 X 151.69 X 151.53	22951	**8.772**	537.5	23.4	22.7
2	FF Roof Concrete	M25	09/01/2021	16/01/2021	149.86 X 150.56 X 151.36	22563	**8.381**	513.3	22.7	
3	FF Roof Concrete	M25	09/01/2021	16/01/2021	151.43 X 151.26 X 151.49	22905	**8.828**	504.1	22.0	

Results obtained are satisfactory as per standard requirements.

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |